

SILICA/HARD POLYMER CLAD Optical Fiber JTFLH

- Low -OH Core
- High NA
- Hard Cladding


Characteristics

- Step Index
- Numerical Aperture: 0.37 ± 0.02
Full Acceptance Cone: 43.4 degrees
- Low -OH Silica Core, Hard Polymer Clad
- Low -OH Core for Vis-NIR Transmission
- Operating Temperature: -65°C to $+125^{\circ}\text{C}$
- Proof Tested from 100kpsi to 150kpsi
- Optional Acrylate, Nylon, or Hytrel[®] Buffer
- Custom NA's Available

JTFLH – Tefzel[®] Buffer

Product Descriptor	Core (μm)	Clad (μm)	Buffer (μm)	Proof Test (kpsi)
JTFLH200230500	200 ± 4	230 +0/-10	500 ± 30	150
JTFLH300330650	300 ± 6	330 +5/-10	650 ± 30	100
JTFLH400430730	400 ± 8	430 +5/-10	730 ± 30	100
JTFLH6006301040	600 ± 10	630 +5/-10	1040 ± 30	100
JTFLH8008301040	800 ± 10	830 ± 10	1040 ± 30	100
JTFLH100010351400	1000 ± 15	1035 ± 15	1400 ± 50	100

Typical Attenuation



Tefzel[®] and Hytrel[®] are registered trademarks of DuPont Corporation.



18019 N. 25th Avenue • Phoenix, AZ 85023-1200
 Voice: (602) 375-4100 Fax: (602) 375-4110
 E-Mail: sales@polymicro.com
 URL: <http://www.polymicro.com>

- Flexible Capillary
- Multimode Optical Fiber
- Specialty Assemblies
- Micro-Components